

SCHEDA TECNICA / TECHNICAL SHEET

ANDINO GT NM 5											
75% BABY ALPACA - 25% NYLON RICICLATO GRS						75% BABY ALPACA - 25% GRS RECYCLED POLYAMIDE					
TARIFFA DOGANALE: 51082090						CUSTOM CODE: 51082090					
UTILIZZO: macchina rettilinea finezza 5-3 ad un capo TIPO DI TINTURA: pretinto e tinto matasse BAGNI DI TINTURA: colori pretinti: minimo 1 scatola kg. 25*/30* e multipli (il supplemento è applicato fino a kg. 100 compresi) colori tinto matasse: kg. 14* - 28* - 58* - 117 - 235 - 470 (* soggette a supplemento) TRATTAMENTO: Per ottenere una mano morbida e vaporosa, si consiglia di effettuare un leggero lavaggio ad acqua ad una temperatura di ca. 30° con ammorbidente e una emulsione siliconica. Asciugare a temperatura non troppo elevata (max 50°). COLORI A CAMPIONE: si CONFEZIONE: colori pretinti: rocche da kg 1 - 1,1 colori uniti : rocche da kg 0,800 circa TIPO E N° DI NODI: splicer : n° 3-4 per rocca ALLUNGAMENTO: (NORM UNI EN ISO 2062) medio: 28% RESISTENZA: (NORM UNI EN ISO 2062) medio: oltre KG 2 VALORE PILLING: (NORMA UNI EN ISO 12945-1) (test di pilling "I.C.I. Pilling Box Tester" - effettuato su telo in maglia rasata con registrazione media) 3 (A 7200 CICLI) SU TELO TRATTATO						KNITTING: flat machine 5-3 one end DYEING METHOD: Top-dyed and on hanks Top dyed colors: minimum one box kgs. 25*/30* and multiple (the surcharge will be invoiced under kgs. 100 included) on hanks colors: Kgs. 14* - 28* - 58* - 117 - 235 - 470 (*surcharge is applicable) FINISHING: To obtain a soft and fluffy hand, we suggest a light treatment in water at a temperature of around of 30° adding softner and silicon emulsion. Centrifuge at low temperature (max 50°C). COSTUMERS OWN COLOURS: yes MAKE UP: mélange colors : cones of about kg 1 - 1,1 each solid colors: cones of about kg 0,800 each TYPE AND NR OF KNOTS: splicer: nr 3-4 each cone TENSILE STRENGTH: (NORM UNI EN ISO 2062) medium: 28% BREAKING FORCE: (NORM UNI EN ISO 2062) medium: more than KG 2 PILLING: (NORM UNI EN ISO 12945-1) (pilling test "I.C.I. Pilling Box Tester" - tested on knitted flat swatch with avr. adjustment): 3 (AT 7200 TURNS) ON FINISHED SWATCH					
SIMBOLOGIA INTERNAZIONALE DI MANUTENZIONE						GARMENT CARE INTERNATIONAL SYMBOLOGY					
CAPI UNITI // PLAIN GARMENTS						CAPI RIGATI // STRIPED GARMENTS					
											
SOLIDITÀ COLORI						COLOR FASTNESS					
Solidità Color Fastness	Lavaggio acqua Water washing		Lavaggio a secco Dry cleaning		Sudore acido Acid Perspiration		Sudore alcalino Alkaline Perspiration		Sfregamento secco Dry rubbing	Sfregamento umido Wet rubbing	Luce Light (WHITE + ECRU =2)
normative	Iso 105-C06		Iso 150-D01		Iso 105-E04		Iso 105-E04		Iso 105-X12	Iso 105-X12	Iso 105-B02
	degradation	discharge	degradation	discharge	degradation	discharge	degradation	discharge	discharge	discharge	discharge
Light col	3-4	3-4	4	3-4	3-4	-	3-4	-	3-4	3-4	4
Med col	3	3	3-4	3-4	3	-	3	-	3-4	3	4
Dark col	3	3	3-4	3-4	3	-	3	-	3	3	4-5
TIPO DI LUCE PER IL TEST COLORE D 65 - DAY LIGHT						LIGHT TYPE FOR COLOUR TEST D 65 - DAY LIGHT					
DATI ECO-TOSSICOLOGICI pH 4.0 – 8.5 NORM ISO 3071						ECO-TOXICOLOGICAL INFORMATION pH 4.0 – 8.5 NORM ISO 3071					
CONTENUTO FORMALDEIDE / Mg/kg < 75 NORM ISO 14184-1						FORMALDEHYDE CONTENT Mg/kg < 75 NORM ISO 14184-1					
AZO FREE SI						AZO FREE YES					
PERCENTUALE DI SCARTO DA TOLLERARE: 5%						WASTE: 5 %					
CONSIGLI ED AVVERTIMENTI: 1) È indispensabile effettuare adeguate prove di lavaggio e stiro su un capo pilota, prima di proseguire con la lavorazione, per verificare il valore dei rientri e la solidità dei colori. 2) Per ottenere una maggiore scorrevolezza ed omogeneità sulle macchine da maglieria, è consigliabile effettuare un'ulteriore parafinitura, in particolare se il filato viene lavorato dopo 10/15 giorni dalla data di consegna. 3) I colori mélange (tinti tops) possono presentare una leggera differenza di tonalità di colore fra partite diverse. 4) La resa e la mano di questo filato, presentano differenze fra i colori mélange (tinti tops) e i colori uniti (tinti in matasse); per questo motivo è opportuno testare ogni colore prima di iniziare la lavorazione. 5) La presenza sporadica di fibre scure naturali visibili su colori molto chiari e di fibre chiare visibili su colori molto scuri è una caratteristica non eliminabile della fibra di alpaca. 6) Prima di confezionare il capo è consigliabile effettuare un pre-stiro su un piatto a vapore, in modo da permettere il regolare rientro dell'elastomero. 7) L'utilizzo del filato per maglieria rigata o comunque con l'utilizzo di più colori, deve essere dichiarato alla stipula dell'ordine; l'INDUSTRIA ITALIANA FILATI non sarà responsabile di eventuali danni derivati dalla inottemperanza di quanto specificato.						IMPORTANT ADVICE: 1) It is absolutely necessary to do a washing and ironing test on a sample garment - to verify shrinkage values and colours fastness - before proceeding with production. 2) If yarn is knitted after more than two weeks from delivery, it is advisable to rewash it in order to achieve a smooth "run" through the needles and a more homogeneous result. 3) Melange colours (top dyed) may show a slight colour tone difference between different dye lots. 4) We suggest you to test each colour before proceeding with the production as some colours have been top dyed while some others have been hank dyed. Melange colours (top dyed) may perform slightly different than the solid ones (hank dyed) - in terms of sizes and handle feeling. 5) The sporadic presence of dark natural hairs visible on very light colors and the presence of light natural hairs visible on very dark colors is a physical characteristic of the alpaca fibre that cannot be avoided. 6) Before packing the garment, it is advisable to pre-iron it on a steam plate in order to regularize the elastomer shrinkage. 7) Whenever yarn is used for STRIPES in contrasting colors, spinner MUST be informed at time of order; INDUSTRIA ITALIANA FILATI will disclaim any responsibility if such information was not given on time.					

THE YARN RESPECT ALL PARAMETERS OF THE REACH REGULATION (1907/2006)

The information hereby reported are to be considered as average values of tests executed in our laboratories. This sheet has to be considered as technical partial support for whom use the yarn. It remain obligation for the company that use the yarn to carry out all the needed controls on the yarns to be able to verify the correspondence to the own requirements. Industria Italiana filati will not be responsible for claims outside the terms previewed from laws and commercial customs.