

SCHEDA TECNICA / TECHNICAL SHEET

CORSA NM 21													
88% VISCOSA - 12% PBT						88% VISCOSE - 12% PBT (POLYESTER)							
TARIFFA DOGANALE: 55113000						CUSTOM CODE: 55113000							
UTILIZZO: macchina rettilinea finezza 12 ad un capo TIPO DI TINTURA: in matasse BAGNI DI TINTURA: kg. 13,5* - 30* - 63* - 126 - 252 - 504 (* soggette a supplemento) TRATTAMENTO: Nessun trattamento particolare COLORI A CAMPIONE: si CONFEZIONE: rocche da kg 1 circa TIPO E N° DI NODI: manuali : n° 2 - 3 per rocca ALLUNGAMENTO: (NORM UNI EN ISO 2062) medio: 22% RESISTENZA: (NORM UNI EN ISO 2062) medio: gr 610 VALORE PILLING: (NORMA UNI EN ISO 12945-1) (test di pilling "I.C.I. Pilling Box Tester" - effettuato su telo in maglia rasata con registrazione media) 3 (A 7200 CICLI) SU TELO TRATTATO						KNITTING: flat machine 12 gauge one ply DYEING METHOD: on hanks OPTIMAL QUANTITY: Kgs. 13,5* - 30* - 63* - 126 - 252 - 504 (* surcharge is applicable) FINISHING: No particular finishing required COSTUMERS OWN COLORS: yes MAKE UP: cones of about kg 1 each TYPE AND NR OF KNOTS: manual; nr 2 - 3 each cone TENSILE STRENGTH: (NORM UNI EN ISO 2062) medium: 22% BREAKING FORCE: (NORM UNI EN ISO 2062) medium: gr 610 PILLING: (NORM UNI EN ISO 12945-1) (pilling test "I.C.I. Pilling Box Tester" - tested on knitted flat swatch with avr. adjustment): 3 (AT 7200 TURNS) ON FINISHED SWATCH							
SIMBOLOGIA INTERNAZIONALE DI MANUTENZIONE						GARMENT CARE INTERNATIONAL SYMBOLOGY							
CAPI UNITI // PLAIN GARMENTS						CAPI RIGATI // STRIPED GARMENTS							
SOLIDITA' COLORI						COLOR FASTNESS							
Solidità Color Fastness	Lavaggio acqua Water washing		Lavaggio a secco Dry cleaning		Sudore acido Acid Perspiration		Sudore alcalino Alkaline Perspiration		Sfregamento secco Dry rubbing		Sfregamento umido Wet rubbing		Luce Light (WHITE + ECRU =2)
normative	Iso 105-C06		Iso 150-D01		Iso 105-E04		Iso 105-E04		Iso 105-X12		Iso 105-X12		Iso 105-B02
	degradation	discharge	degradation	discharge	degradation	discharge	degradation	discharge	discharge	discharge	discharge	discharge	
Light col	4	4	4	4	3-4	-	3-4	-	4	3-4	3-4	3-4	4
Med col	3-4	3-4	3-4	3-4	3	-	3	-	3-4	3	3	3	4
Dark col	3	3	3-4	3-4	3	-	3	-	3	3	3	3	4-5
TIPO DI LUCE PER IL TEST COLORE D 65 - DAY LIGHT						LIGHT TYPE FOR COLOR TEST D 65 - DAY LIGHT							
DATI ECO-TOSSICOLOGICI pH 4.0 – 8.5 NORM ISO 3071						ECO-TOXICOLOGICAL INFORMATION pH 4.0 – 8.5 NORM ISO 3071							
CONTENUTO FORMALDEIDE / Mg/kg < 75 NORM ISO 14184-1						FORMALDEHYDE CONTENT Mg/kg < 75 NORM ISO 14184-1							
AZO FREE SI						AZO FREE YES							
PERCENTUALE DI SCARTO DA TOLLERARE: 5%						WASTE: 5 %							
CONSIGLI ED AVVERTIMENTI: 1) È indispensabile effettuare adeguate prove di lavaggio e stiro su un capo pilota, prima di proseguire con la lavorazione, per verificare il valore dei rientri e la solidità dei colori. 2) Per ottenere una maggiore scorrevolezza ed omogeneità sulle macchine da maglieria, è consigliabile effettuare un'ulteriore paraffinatura, in particolare se il filato viene lavorato dopo 10/15 giorni dalla data di consegna. 3) Date le caratteristiche di elasticità del prodotto, è importante smacchinare il filato sempre nelle stesse condizioni di lavoro (tensioni, regolazione del punto, velocità della macchina) per non incorrere in variazioni di resa dei teli. 4) L'utilizzo del filato per maglieria rigata o comunque con l'utilizzo di più colori, DEVE essere dichiarato alla stipula dell'ordine; l'INDUSTRIA ITALIANA FILATI non sarà responsabile di eventuali danni derivati dalla inottemperanza di quanto specificato						IMPORTANT ADVICE: 1) It is absolutely necessary to do a washing and ironing test on a sample garment - to verify shrinkage values and colours fastness - before proceeding with production. 2) If yarn is knitted after more than two weeks from delivery, it is advisable to rewash it in order to achieve a smooth "run" through the needles and a more homogeneous result. 3) This stretch yarn must always be knitted with the same standard registration (tension, stitch, machine speed etc.) used when knitting sample garment. This will avoid risk of having panels out-of-standard. 4) Whenever yarn is used for STRIPES in contrasting colors, spinner MUST be informed at time of order; INDUSTRIA ITALIANA FILATI will disclaim any responsibility if such information was not given on time.							

CLASSIFICAZIONE COLORI: COLORS CLASSIFICATION:

C = CHIARI / LIGHT
M = MEDI / MEDIUM
S = SCURI / DARK

THE YARN RESPECT ALL PARAMETERS OF THE REACH REGULATION (1907/2006)

The information hereby reported are to be considered as average values of tests executed in our laboratories. This sheet has to be considered as technical partial support for whom use the yarn. It remain obligation for the company that use the yarn to carry out all the needed controls on the yarns to be able to verify the correspondence to the own requirements. Industria Italiana filati will not be responsible for claims outside the terms previewed from laws and commercial customs.